



Productspecification/Information

EDEL SOCCER BLADE PRO 2.0 - 25

A	Name of product Sports application	EDEL SOCCER BLADE PRO 2.0 - 25 Football, Soccer
B	Producer Production process	EDEL GRASS B.V. - Genemuiden - The Netherlands tufted, cut pile
C	Pile material Yarn Dtex Cross-section of tapes Colour Line colour UV-stability Light fastness Colour fastness	Thiolon® PE 12500 monofilament MS Classic polyethylene + MS EG polyethylene yarn , knit-de-knit, thermofixated micro curl environment friendly, UV-stabilised 12500/6 Dtex + 8500/12 Dtex width : 1.5 mm / 0.55 mm, ±5% thickness : 240 µm / 205 µm , ±5% field green and limegreen white DIN 53387 meets 6000 hours W.O.M. test >7 on blue scale 1-8 >4 on gray scale 1-5
D	Primary backing Coating Water permeability	Thiobac® polypropylene glas reinforced, UV-stabilised, total weight ± 335 gr/m ² Carboxylated (SBR) latex, appr. 1444 gr/m ² with 4mm perforation holes > 180 mm/h
E	Product details Pile height Total construction height Pile weight Total weight Gauge Stitch per m ¹ linear Stitch per m ² Filaments per m ²	appr. 25 mm ±10% appr. 27 mm ±10% appr. 2315 gr/m ² ±10% appr. 4094 gr/m ² ±10% 3/8" 180 ±10 18.900 ±10% 680.400 ±10%
F	Infill Stabilizing infill Amount Performance infill Amount	N.A N.A
G	Installation method Roll width Roll length Joints/seams Line marking	loose laid on bound or unbound sub-base with loose laid shockpad or in situ E-layer 4 m ¹ (± 2 cm) according to installation schedule the seams in the turf are joined with a reinforcing tape type 220 glued to the back of the turf tufted-in or to be laid in by installation

The above data are subject to modifications based on technical improvements or company-internal developments. All data are higher than the DIN-standards. All figures are average values and can vary slightly.

